

S. V COATINGS PVT LTD

200/B, Suncity Road, K.S.Town, Bangalore-560060



ISO 9001:2008

Reg. No.: RQ91/5547

POLYVAR-510

Technical Data Sheet

A signal pack, acrylic based quick drying enamel, has good gloss retention properties, good adhesion to metal, plastic, fiberglass etc.

Colour	Range
Solids	50+/- 5
Coverage	11-12 sq mts/ltr/coat
Viscosity	55-65 sec at 30 deg Centigrade
Drying Time	Surface Dry 3-5 mints Hard dry 4-6 hrs
Flash point	Above 30 deg Centigrade
Recommended dry film thickness	20 to 25 microns
Method of application	Brush / Spray
Interval before over coating	2 hr minimum
Surface preparation	Requires wire brushing or acid pickling/ followed by phosphate
Uses	Automotive components, Solar water heaters, Machineries, Industrial conveyers, Dental equipments, etc.
Thinner	Polyvar-31
Storage life	9 months

Disclaimer : To the best of our Knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product. We do not accept any responsibility or liability arising out of use of the product. The Company reserves the right to modify data contained herein without prior notice.

November 2009