

S. V COATINGS PVT LTD

Technical Data Sheet

POLYVAR--610

A signal pack alkyd based paint having good gloss, mar resistance, suitable for general purpose coating.

Colour	All colours
Solids	50+/- 2
Coverage	13-4 sq mts/ltr/coat
Viscosity	180-200 sec at 30 deg Centigrade
Drying Time	Surface Dry 2-3 Hrs
Flash point	Above 30 deg Centigrade
Recommended dry film thickness	25 to 30 microns
Method of application	Brush / Spray
Interval before over coating	12 hr minimum
Surface preparation	Requires wire brushing or acid pickling/ followed by phosphate
Uses	General purpose coating.
Thinner	Polyvar-31 for spray application Polyvar -30 for brush application
Storage life	9 month

Disclaimer : To the best of our Knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product. We do not accept any responsibility or liability arising out of use of the product. The Company reserves the right to modify data contained herein without prior notice.

November 2016