

S. V COATINGS PVT LTD

200/B, Suncity Road, K.S.Town,
Bangalore-560060



ISO 9001:2008

Reg. No.: RQ91/5547

Technical Data Sheet

POLYVAR--611

A high performance single pack Red oxide / yellow oxide primer. The version contains red oxide of iron or yellow oxidete. It is compatible with a wide range of top coats. The primer gives excellent adhesion to steel.

Colour	Red Oxide/ yellow
finish	Matt to eggshell
Solids	50 +/- 5
Coverage	15-16 sq mts/ltr/coat
Drying Time	Touch Dry 2-3 hours Handleable in 6-8 Hours
Flash point	Above 30 deg Centigrade
Recommended dry film thickness	30-40 Microns Per coat.
Method of application	Brush / Spray
Interval before over coating	8 hr minimum
Surface preparation	Requires wire brushing or acid pickling.
Uses	General maintenance primer for Marine Installations, fertilizer plants, pulp & paper mills, bridges, Engineering Industries, power plants, ship construction, oil Refineries, etc .
Thinner	Polyvar-31
Storage life	9 months

Disclaimer : To the best of our Knowledge the information provided herein are true and accurate at the date of issunce. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product. We do not accept any responsibility or liability arising out of use of the product. The Company reserves the right top modify data contained herein without prior notice.

November 2009