

# S. V COATINGS PVT LTD

37/a, 4<sup>th</sup> Cross, Sri Satyasainagar, Kodipalya , Kengeri, Bangalore-560060  
Pn.32915084 / 9343729849

## Technical Data Sheet

### **POLYVAR-701**

A signal pack phenolic based anticorrosive paint having good resistance to moisture, light acids and alkalis mar resistance, suitable for under chassis, marine and maintaince coating.

Colour	Selected shades
Solids	52+/- 2
Coverage	13-4 sq mts/ltr/coat
Viscosity	120-150 sec at 30 deg Centigrade
Drying Time	Surface Dry 45-60 mints
Flash paint	Above 30 deg Centigrade
Recommended dry film thickness	20 to 25 microns
Method of application	Brush / Spray/dip
Interval before over coating	4 hr minimum
Surface preparation	Requires wire brushing or acid pickling/ followed by phosphate
Uses	General purpose coating.
Thinner	Polyvar-30 for spray application Polyvar -30 for brush application
Storage life	9 month

Disclaimer : To the best of our Knowledge the information provided herein are true and accurate at the date of issusnce. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product. We do not accept any responsibility or liability arising out of use of the product. The Company reserves the right top modify data contained herein without prior notice.

November 2008