

S. V COATINGS PVT LTD

Technical Data Sheet

POLYVAR-EPXY-911

A high performance two pack epoxy primer specially formulated by using red oxide pigment. It is compatible with a wide range of epoxy top coats. It forms heavy duty coating system for metal surface. The coating remains unaffected by many corrosive chemicals and solvents and render durable finish in industrial and marine atmosphere.

| | |
|--------------------------------|--|
| Colour | Grey / Red Oxide |
| Solids | 60+/- 5 |
| Coverage | 12-14 sq mts/ltr/coat |
| Mixing ratio in volume | Base : Accelerator – 4:1 |
| Pot Life | 4-6 hours |
| Drying Time | Touch Dry 2-4 hours Handleable in 8 Hours Full Curing in 7-8 days. |
| Flash point | Above 30 deg Centigrade |
| Recommended dry film thickness | 30-40 Microns Per coat. |
| Method of application | Brush / Spray |
| Interval before over coating | 8 hr minimum 7-8 days Maximum |
| Surface preparation | Requires wire brushing or acid pickling/ followed by sand blasting. |
| Uses | Marine Installations, fertilizer plants, pulp & paper mills, bridges, Engineering Industries, power plants, ship construction, oil Refineries, etc . |
| Thinner | Polyvar-31 |
| Storage life | 9 month |

Disclaimer : To the best of our Knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product. We do not accept any responsibility or liability arising out of use of the product. The Company reserves the right to modify data contained herein without prior notice.

November 2016